



Z-Tech LLC
8 Dow Road
Bow, NH 03304 USA

Tel. No.: 603.228.1305
Fax No.: 603.228.5234

Monoclinic Zirconia Produced Via the Plasma Arc Process

TYPICAL PROPERTIES

GRADE	% ZrO ₂ +HfO ₂	% SiO ₂	Avg. Particle Size
CF-COLORTONE	67.5	31.6	105 microns
CF-PREMIUM	96.4	2.70	60 microns
CF-PREMIUM-M	96.4	2.70	27 microns
CF-EXTRA	98.6	0.90	95 microns
CF-PLUS	98.6	0.90	13 microns
CF-PLUS-HM	98.6	0.90	1.6 microns
CF-SUPER	99.2	0.50	7.0 microns
CF-SUPER-HM	99.2	0.50	1.3 microns
EF-PREMIUM	99.4	0.25	1.2 microns
EP-EXTRA	99.5	0.18	1.0 microns
EF-EXTRA	99.6	0.12	1.0 microns
SF-PREMIUM	99.4	0.25	1.2 microns
SF-EXTRA	99.6	0.12	1.0 microns

For more detailed information, please contact us at Zirpro@saint-gobain.com